

ORGANIC BLANKETS FOR EROSION CONTROL

- Absorb the kinetic energy produced by the erosive particle –water drops, wind, snow, etc.-
- Increase water retention capacity of the soil since they avoid water loss due to evaporation.
- Regulate the soil temperature since they protect it from heat and cold exposure.
- Become a component of the soil itself developing into an organic horizon.
- Complement to auxiliary elements in the public work like curbs, ditches, etc
- Reduce the conservation costs because they avoid soil losses which filled and damaged drainages and ditches.
- High performance and complete landscaping integration.
- Easy installation and low costs

BONTERRA 3KR

(COIR TRIPLE DENSITY. ORGANIC BLANKET. DOUBLE REINFORCED NETTING)

TECHNICAL DATA

Applications	<ul style="list-style-type: none"> - Ditches and rills - Moderate ditch erosion ($V < 1.5$ m/s) - Windbreaks - Slopes - Climbing plants support 	
Composition	Natural: 100% coir (Approx. Density: 566- 766 g/m ²) Sinhtetical : polipropylene (Density 83,33 g/m ²)	
Presentation	In Rolls	Length: 40m. Width: 2m. Approx. Diameter: 0,60m.
Structure	Thread: Polipropylene (PP) 1000 den Netting on both sides: polipropylene (PP)	Weight: 3,33g/m ² . Colour: negro. Toughness: 4,12g/den Bottom netting: Black polipropylene. Weight: 40 g/m ² Mesh size: 25,00 mm x 27,00 mm Lengthwise tensile strength: 2,90 KN/m Crosswise tensile strength: 1,90 KN/m Top netting: Black polipropylene Weight: 40 g/m ² Mesh size: 25,00 mm x 27,00 mm Lengthwise tensile strength: 2,90 KN/m Crosswise tensile strength : 1,90 KN/m
Average breaking strength	Lengthwise: 9,97 KN/m Crosswise: 6,48 KN/m	

BonTerra Ibérica: *Efficiency against erosion*

BonTerra is member of:

C/ Atlanta, 4 - Bajo. Portal C
 18014 Granada España
 Tel.: +34 902 200 502 Fax: +34 958 172 285
 tecnico@bonterraiberica.com



WIDE- WIDTH TENSILE TEST

Standard: UNE EN ISO 10319:1996

Apparatus: INSTRON Dynamometer

Direction	Average breaking strength (KN/m)	C.V.(%)	Extension at max. load (%)	C.V.(%)
Lengthwise	9.97	7.5	30.42	20.7
Crosswise	6.48	6.5	80.59	7.9

Direction	Percentage	Average secant module (KN/m)	C.V. (%)
Lengthwise	2%	40.5	46.5
	5%	47.7	31.4
	10%	52.85	17.8
Crosswise	2%	34	50.1
	5%	35	30.5
	10%	33.9	14.7

Direction	Rate of deformation (%/ min.)
Lengthwise	20
Crosswise	19

BonTerra Ibérica: Efficiency against erosion

BonTerra is member of:

C/ Atlanta, 4 - Bajo. Portal C
 18014 Granada España
 Tel.: +34 902 200 502 Fax: +34 958 172 285
 tecnico@bonterraiberica.com

